




Tairus Supra Orange 2GL-T

Exhaustion Dyeing 浸染




Dyes Properties 染料特性

Classification S.D.C.分類	Levelling 均染性	Solubility 80 °C 溶解度	Liquor ratio 浴 比	High Temp. 高溫染色	Build up 上色性
B	◎	100 g/l	◎	◎	◎

Exhaustion 浸染適性	Continuous 連染適性	Printing 印花適性
◎	◎	◎

Staining on 纖維污染					
Cotton	Nylon	Wool	Rayon	Acrylic	PES
1	3	1~2	1	4~5	5





Tairus Supra Orange 2GL-T

Washing Properties 水洗特性 (2.0 % o.w.f.)

49°C (AATCC 61 2A) 49°C 耐水洗						Water 耐水	
Acetate	Cotton	Nylon	Polyester	Acrylic	Wool	Alter 色變	Cotton污染
5	3	4~5	5	5	5	4~5	5

60°C (M&S C4A) 60°C 耐水洗						See Water 耐海水	
Acetate	Cotton	Nylon	Polyester	Acrylic	Wool	Alter 色變	Cotton污染
5	2~3	4~5	5	5	5	5	5

Color Fastness 堅牢度 (2.0 % o.w.f.)

Dry Cleaning 耐乾洗		Chlorine Water 耐氯水		Perspiration 耐汗 Acid 酸	
Alter 色變	Cotton污染	Alter 色變	Cotton污染	Alter 色變	Cotton污染
5	5	4Y	5	5	5

Light 耐光		Rubbing 耐摩擦		Perspiration 耐汗 Alkaline 鹼	
0.2 % o.w.f.	2.0 % o.w.f.	Dry 乾	Wet 濕	Alter 色變	Cotton污染
4~5	5	4~5	4	5	5

Printing Properties 印花特性

Reduction agent 還原劑 Dischargeability 拔染性	Dependence on Steaming 蒸處依存性		Dependence on Steaming Process 適用蒸處方式	
◎	Temperature	Time	HPS	HTS
	◎~○	◎	◎	○

T & T LABORATORY TECHNICAL DATA

Chief	Tester	Date	Data No.
Michael 104.10.24 B5/20063-001			

Proposal


2/2

Material: Cotton 100%

Process: Dyeing (100°C X 50') S-300 1g/l (40°C X 15') → Dyefix Dr-119 4% (60°C X 20') Ph5

Results:

Tairus Supra Orange 2GL-T



Staining Test



Washing Fastness (AATCC2A)

2.00%



Perspiration Fastness Test (37±2°C X 4 hours) 2.00%

Acid

Alkaline



Water Fastness Test (37±2°C X 4 hours)

2.00%



Sea Water Fastness Test (37±2°C X 4 hours)

2.00%




Light Fastness Test 40 hours

Untreat

Treat

0.50%

2.00%



Rubbing Test 2.00%

Dry

Wet

