

Chief	Tester	Date	Data No.
鍾招平	張雅屏	113.01.30C	4010037

Proposal

Material: A)100% CDP 75D/72F (T&T)  
 B) 88% CDP 100D/144F + OP 12% (T&T)


Process: A)Dyeing ( 120°C X 30' )  
 B)Dyeing ( 120°C X 50' )

Recipe:

Pantone 13-1023

A)  
 Taiacryl Yellow AD-RST 0.139%  
 Taiacryl Red AD-2GLT 0.027%

PH4



Washing Fastness Test(AATCC2A)

Before After

T&T MIX A)




Ace C N Pet Ac W

Pantone 13-1023

B)  
 Taiacryl Yellow AD-RST 0.122%  
 Taiacryl Yellow AD-3RLT 0.014%  
 Taiacryl Red AD-2GLT 0.0242%

PH4



Washing Fastness Test(AATCC2A)

Before After

T&T MIX B)



Ace C N Pet Ac W